

## CLAIMS

1. A (meth)acryloyloxyalkyl isocyanate containing a dissolved acidic gas (excluding hydrogen chloride).

5           2. A (meth)acryloyloxyalkyl isocyanate containing an acidic gas (excluding hydrogen chloride) forcedly dissolved in the (meth)acryloyloxyalkyl isocyanate in an amount sufficient for stabilizing the (meth)acryloyloxyalkyl isocyanate.

10

3. The (meth)acryloyloxyalkyl isocyanate according to claim 1 or 2 in which the acidic gas is dissolved in an amount of not less than 20 ppm based on the (meth)acryloyloxyalkyl isocyanate.

15

4. The (meth)acryloyloxyalkyl isocyanate according to claim 3 which has a hydrolyzable chlorine content of not more than 30 ppm based on the (meth)acryloyloxyalkyl isocyanate.

20

5. The (meth)acryloyloxyalkyl isocyanate according to claim 4 which is prepared by using phosgene.

6. The (meth)acryloyloxyalkyl isocyanate according

to any one of claims 1 to 5 wherein the acidic gas is carbon dioxide.

7. The (meth)acryloyloxyalkyl isocyanate according to any one of claims 1 to 6 wherein the (meth)acryloyloxyalkyl isocyanate is (meth)acryloyloxyethyl isocyanate.

8. A process for stabilizing a (meth)acryloyloxyalkyl isocyanate, which process comprises forcedly dissolving an acidic gas (excluding hydrogen chloride) in the (meth)acryloyloxyalkyl isocyanate.

9. The process for stabilizing a (meth)acryloyloxyalkyl isocyanate according to claim 8 wherein the (meth)acryloyloxyalkyl isocyanate is a high purity (meth)acryloyloxyalkyl isocyanate which is prepared by decreasing the amount of hydrolyzable chlorine with purification.

20

10. The process for stabilizing a (meth)acryloyloxyalkyl isocyanate according to claim 9 wherein the (meth)acryloyloxyalkyl isocyanate is prepared by using phosgene.

11. The process for stabilizing a  
(meth)acryloyloxyalkyl isocyanate according to any one of  
claims 8 to 10 wherein the acidic gas is carbon dioxide.

5

12. The process for stabilizing a  
(meth)acryloyloxyalkyl isocyanate according to any one of  
claims 8 to 11 wherein the (meth)acryloyloxyalkyl  
isocyanate is (meth)acryloyloxyethyl isocyanate.

10

13. A process for preparing a stabilized  
(meth)acryloyloxyalkyl isocyanate , which process  
comprises forcedly dissolving an acidic gas (excluding  
hydrogen chloride) in a (meth)acryloyloxyalkyl isocyanate.

15

14. The process for preparing a stabilized  
(meth)acryloyloxyalkyl isocyanate according to claim 13,  
wherein the (meth)acryloyloxyalkyl isocyanate is a high  
purity (meth)acryloyloxyalkyl isocyanate prepared by  
decreasing the amount of hydrolyzable chlorine with  
purification.

20

15. The process for preparing a stabilized  
(meth)acryloyloxyalkyl isocyanate according to claim 14,

wherein the (meth)acryloyloxyalkyl isocyanate is prepared by using phosgene.

16. The process for preparing a stabilized  
5 (meth)acryloyloxyalkyl isocyanate, according to any one of claims 13 to 15 wherein the acidic gas is carbon dioxide.

17. The process for preparing a stabilized  
(meth)acryloyloxyalkyl isocyanate, according to any one of  
10 claims 13 to 16 wherein the (meth)acryloyloxyalkyl isocyanate is (meth)acryloyloxyethyl isocyanate.